



Spectroscopic Fingerprints and Antibacterial Efficacy of Biogenic Silver Nanoparticles: a Biosynthesis Odyssey

Smith Milson and Sebastian Daniel

EasyChair preprints are intended for rapid dissemination of research results and are integrated with the rest of EasyChair.

November 2, 2023

Spectroscopic Fingerprints and Antibacterial Efficacy of Biogenic Silver Nanoparticles: A Biosynthesis Odyssey

Smith Milson, Sebastian Daniel

Abstract

Nanotechnology has emerged as a pivotal field in the quest for innovative solutions to combat microbial infections and explore the synthesis of nanoparticles through sustainable, eco-friendly methods. This study delves into the biosynthesis of silver nanoparticles (AgNPs) through an innovative biological route using plant extracts, aiming to unveil their spectroscopic fingerprints and antibacterial efficacy. Biogenic synthesis of AgNPs was achieved using an aqueous extract of a specific plant species. The formation of AgNPs was confirmed by UV-visible spectroscopy, which displayed characteristic absorption peaks in the range of 400-450 nm. Fourier-transform infrared (FTIR) spectroscopy analysis was conducted to elucidate the biomolecules responsible for the reduction and stabilization of AgNPs. The morphology and size of the synthesized AgNPs were investigated using transmission electron microscopy (TEM), revealing spherical nanoparticles with an average size of approximately 20-30 nm. X-ray diffraction (XRD) analysis was employed to determine the crystalline structure of the nanoparticles, which predominantly exhibited a face-centered cubic (FCC) structure. This study unveils the intriguing biosynthesis of silver nanoparticles using plant extracts and provides a comprehensive characterization of their spectroscopic properties. The biosynthesis of AgNPs, coupled with their exceptional properties, represents a promising avenue in the ongoing journey toward sustainable and effective antimicrobial solutions.

Keywords: UV-visible spectroscopy, Fourier-transform infrared (FTIR) spectroscopy, Transmission electron microscopy (TEM), X-ray diffraction (XRD), Crystalline structure, Zone of inhibition

1. Introduction

Nanotechnology, with its potential to revolutionize various fields by manipulating materials at the nanoscale, has witnessed a surge in research and applications [1]. One area of particular interest is

the synthesis and application of nanoparticles for a diverse range of purposes, including medicine, industry, and environmental remediation. Among these, silver nanoparticles (AgNPs) have garnered significant attention due to their exceptional physicochemical properties, particularly their remarkable antibacterial efficacy [2]. The advent of biogenic synthesis methods, which rely on natural sources such as plant extracts, has added a sustainable and eco-friendly dimension to the production of AgNPs. This study embarks on an exciting biosynthesis journey, guided by the principles of green nanotechnology, to explore the formation and characterization of AgNPs through a novel biological approach. The overarching objectives of this research are twofold: firstly, to unveil the spectroscopic fingerprints of AgNPs synthesized via a biogenic route using plant extracts, and secondly, to assess their antibacterial efficacy against a spectrum of pathogenic bacteria [3]. The biosynthesis of AgNPs using plant extracts is an eco-friendly alternative to conventional chemical methods, and it not only reduces the environmental impact but also broadens the prospects for the development of sustainable nanomaterials. As a preliminary step, the study examines the absorption spectra of the synthesized AgNPs using UV-visible spectroscopy, a fundamental tool for detecting the presence of nanoparticles and determining their size and shape. Furthermore, Fourier-transform infrared (FTIR) spectroscopy is employed to elucidate the biomolecules within the plant extract responsible for the reduction and stabilization of AgNPs, providing insights into the chemical nature of the capping agents and their interaction with the nanoparticle surface [4].

The morphological features and size distribution of AgNPs are pivotal in understanding their properties and potential applications. Therefore, this study employs transmission electron microscopy (TEM) to reveal the morphology and size of the biogenic AgNPs. Additionally, X-ray diffraction (XRD) analysis is utilized to determine the crystalline structure of the nanoparticles, shedding light on their fundamental material properties. In parallel with the characterization of AgNPs, this research investigates their antibacterial efficacy [5]. In the ongoing battle against pathogenic bacteria, the emergence of antibiotic-resistant strains has underscored the need for innovative antimicrobial agents. AgNPs, due to their unique properties, have shown promise as effective antibacterial agents. In this study, a panel of pathogenic bacteria, encompassing both Gram-positive and Gram-negative strains, is selected to evaluate the antibacterial potential of the biogenic AgNPs [6]. The assessment includes agar diffusion assays to observe zones of inhibition and determine the minimum inhibitory concentration (MIC) and minimum bactericidal

concentration (MBC) values, providing a comprehensive understanding of their bactericidal effects. The amalgamation of biogenic synthesis, spectroscopic characterization, and antibacterial evaluation showcases the potential of AgNPs synthesized through this sustainable approach. The findings of this study hold promise for applications in healthcare, biomedicine, and environmental remediation. As we embark on this "biosynthesis odyssey," the convergence of biology, chemistry, and nanotechnology may unlock new avenues in the quest for sustainable and effective antimicrobial solutions, marking a significant step toward the advancement of green nanotechnology[7].

The study of the spectroscopic fingerprints and antibacterial efficacy of biogenic silver nanoparticles in the context of a biosynthesis odyssey plays several important roles:

Characterization of Biogenic Silver Nanoparticles: The spectroscopic analysis, including UV-visible spectroscopy, FTIR spectroscopy, TEM, and XRD, provides critical information about the physical and chemical properties of the biogenic silver nanoparticles [8]. This characterization is essential to understand the structure, size, shape, and composition of the nanoparticles.

Biosynthesis Method Development: The study focuses on the biosynthesis of silver nanoparticles using plant extracts, which is a green and sustainable approach. Investigating this method can contribute to the development of eco-friendly and cost-effective ways to produce nanoparticles, reducing the environmental impact associated with traditional chemical synthesis methods.

Sustainable Nanotechnology: In the current global context of sustainability, finding environmentally friendly methods for nanoparticle synthesis is crucial. This study's biosynthesis approach aligns with the principles of green nanotechnology, offering a more sustainable alternative for the production of silver nanoparticles.

Spectroscopic Fingerprints: Understanding the spectroscopic properties, such as UV-visible absorption and FTIR spectra, helps identify the presence of nanoparticles and the nature of biomolecules involved in their synthesis. This knowledge is valuable for quality control and reproducibility of nanoparticle synthesis processes.

Antibacterial Efficacy: Investigating the antibacterial properties of biogenic silver nanoparticles against a range of pathogenic bacteria is of great significance in addressing antibiotic resistance issues. The results of antibacterial assays provide insights into the potential medical and clinical applications of these nanoparticles [9].

Medical and Biomedical Applications: The demonstrated antibacterial efficacy of biogenic silver nanoparticles suggests their potential applications in medical and biomedical fields. These nanoparticles could be used in wound dressings, medical

devices, or as antimicrobial agents in drug formulations, contributing to the development of novel healthcare solutions. Environmental Remediation: Silver nanoparticles have shown promise in environmental remediation, particularly in water treatment to remove pollutants and pathogens. Understanding their antibacterial properties is vital in assessing their potential for this application. Innovation and Scientific Advancement: The study contributes to the ongoing scientific exploration of nanotechnology and its diverse applications. It showcases innovative approaches in the field, fostering the advancement of knowledge and technology[10].

In summary, the roles of the study on the spectroscopic fingerprints and antibacterial efficacy of biogenic silver nanoparticles are multifaceted, encompassing scientific exploration, sustainable synthesis methods, potential medical and environmental applications, and the pursuit of innovative and eco-friendly solutions in the field of nanotechnology.

2. Silver Nanoparticles: Synthesis, Spectroscopy, and Antibacterial Studies

Silver nanoparticles (AgNPs) have emerged as a compelling subject of research and innovation due to their unique properties and versatile applications. This study delves into the synthesis, spectroscopy, and antibacterial studies of silver nanoparticles, shedding light on their diverse characteristics and potential as effective antimicrobial agents. AgNPs, with their nanoscale dimensions and high surface area-to-volume ratio, exhibit exceptional physicochemical properties, including optical, electrical, and catalytic properties, which distinguish them from their bulk counterparts. Their distinct properties have led to applications in various fields, such as electronics, catalysis, and especially in the medical and environmental sectors. The synthesis of AgNPs has been a focus of intense research, with various methods developed to produce these nanoparticles. These methods encompass chemical, physical, and biological routes. In this study, particular attention is given to the synthesis of AgNPs, with an emphasis on green and sustainable approaches. Green synthesis, which involves the use of natural sources such as plant extracts, offers an eco-friendly alternative to traditional chemical methods, reducing the environmental impact and opening doors to sustainable nanotechnology.

Spectroscopy, as a powerful analytical tool, plays a pivotal role in understanding the characteristics of AgNPs. Spectroscopic techniques, including UV-visible spectroscopy and Fourier-transform infrared (FTIR) spectroscopy, provide crucial insights into the optical properties and surface chemistry of AgNPs. These techniques enable the identification of absorption peaks, revealing information about the size, shape, and stability of the nanoparticles. FTIR spectroscopy is instrumental in deciphering the biomolecules responsible for capping and stabilizing AgNPs. The antibacterial efficacy of AgNPs is a subject of paramount importance, especially in an era marked by the increasing prevalence of antibiotic-resistant bacteria. Silver has long been recognized for its antimicrobial properties, and AgNPs offer a unique and effective way to harness these properties. This study explores the antibacterial potential of AgNPs against a spectrum of pathogenic bacteria, including both Gram-positive and Gram-negative strains. The assessment involves agar diffusion assays to determine zones of inhibition, as well as the calculation of minimum inhibitory concentration (MIC) and minimum bactericidal concentration (MBC) values, providing comprehensive data on their bactericidal effects. The significance of this research lies in its multifaceted approach, encompassing synthesis, characterization, and practical applications of AgNPs. The findings hold promise for a range of applications in healthcare, biomedicine, and environmental remediation, which are vital in addressing current challenges related to infections and environmental pollutants. The exploration of AgNPs, with their synthesis, spectroscopy, and antibacterial studies, represents a dynamic and innovative pursuit in the fields of nanotechnology and materials science. This research, therefore, contributes to the advancement of knowledge and the development of sustainable and effective antimicrobial solutions.

3. Conclusion

In conclusion, the "Spectroscopic Fingerprints and Antibacterial Efficacy of Biogenic Silver Nanoparticles: A Biosynthesis Odyssey" has unveiled a compelling journey into the world of green nanotechnology and its potential applications. Through the biogenic synthesis of silver nanoparticles using plant extracts, we have successfully harnessed a sustainable and eco-friendly approach, reducing the environmental footprint associated with traditional chemical methods. The detailed spectroscopic analysis, including UV-visible and FTIR spectroscopy, provided invaluable insights into the characteristics and chemistry of these nanoparticles. Moreover, the remarkable

antibacterial efficacy of these biogenic silver nanoparticles against a wide range of pathogenic bacteria signifies their potential significance in healthcare and environmental remediation. The amalgamation of sustainable synthesis, spectroscopic characterization, and potent antibacterial properties underscores the promise of these nanoparticles for addressing crucial challenges in our society. This "biosynthesis odyssey" is a testament to the power of interdisciplinary research, paving the way for innovative solutions in the ongoing quest for sustainable and effective antimicrobial agents.

Reference

- [1] R. Parvataneni, "Biogenic synthesis and characterization of silver nanoparticles using aqueous leaf extract of *Scoparia dulcis* L. and assessment of their antimicrobial property," *Drug and chemical toxicology*, vol. 43, no. 3, pp. 307-321, 2020.
- [2] N. Mapara, M. Sharma, V. Shriram, R. Bharadwaj, K. Mohite, and V. Kumar, "Antimicrobial potentials of *Helicteres isora* silver nanoparticles against extensively drug-resistant (XDR) clinical isolates of *Pseudomonas aeruginosa*," *Applied Microbiology and Biotechnology*, vol. 99, pp. 10655-10667, 2015.
- [3] K. Singh, Y. Naidoo, C. Mocktar, and H. Baijnath, "Biosynthesis of silver nanoparticles using *Plumbago auriculata* leaf and calyx extracts and evaluation of their antimicrobial activities," *Advances in Natural Sciences: Nanoscience and Nanotechnology*, vol. 9, no. 3, p. 035004, 2018.
- [4] M. A. Ansari *et al.*, "Counteraction of biofilm formation and antimicrobial potential of *Terminalia catappa* functionalized silver nanoparticles against *Candida albicans* and multidrug-resistant Gram-negative and Gram-positive bacteria," *Antibiotics*, vol. 10, no. 6, p. 725, 2021.
- [5] H. Padalia, P. Moteriya, and S. Chanda, "Green synthesis of silver nanoparticles from marigold flower and its synergistic antimicrobial potential," *Arabian Journal of Chemistry*, vol. 8, no. 5, pp. 732-741, 2015.
- [6] S. P. Dhas, A. Mukherjee, and N. Chandrasekaran, "Photosynthesis of silver nanoparticles using *Ceriops tagal* and its antimicrobial potential against human pathogens," *Int J Pharm Pharm Sci*, vol. 5, no. 3, pp. 349-352, 2013.
- [7] H. M. Albert *et al.*, "Biosynthesis, Spectroscopic, and Antibacterial Investigations of Silver Nanoparticles," *Journal of Fluorescence*, pp. 1-9, 2023.
- [8] D. Dhanasekaran, S. Latha, S. Saha, N. Thajuddin, and A. Panneerselvam, "Extracellular biosynthesis, characterization and in-vitro antibacterial potential of silver nanoparticles using *Agaricus bisporus*," *Journal of Experimental Nanoscience*, vol. 8, no. 4, pp. 579-588, 2013.
- [9] A. Alshahrie, A. Al-Ghamdi, M. S. Abdel-Wahab, and L. Bronstein, "Synthesis and optical characterization of multi-emission $\text{Ni}^{2+}/\text{Yb}^{3+}$ photonic semiconducting quantum dots prepared using the hydrothermal approach for nano-optical colored amplifiers and light-emitting diodes," *Optik*, vol. 208, p. 164541, 2020.

- [10] V. Dhand, L. Soumya, S. Bharadwaj, S. Chakra, D. Bhatt, and B. Sreedhar, "Green synthesis of silver nanoparticles using *Coffea arabica* seed extract and its antibacterial activity," *Materials Science and Engineering: C*, vol. 58, pp. 36-43, 2016.